

# Install a Rainwater Tank



## Project Cost Estimator

Materials Description	Quantity	Cost
Rainwater Tank		
Rain Head		
PVC Pipes		
PVC Bends/Connectors		
First Flush System		
Pump		
Ball Cock Tap		
PVC Adhesives		
Gutterguard Mesh		
<b>Equipment</b>		
Rake & Shovel		
Adjustable Wrench		
Drill/Driver		
Spirit Level		
<b>Total</b>		

All the above materials and equipment are available at all Magnet Mart Stores.

Note: Due to the general nature of this advice and its individual application, neither the publisher nor the retailer assumes any responsibility for any loss, damage, injury or expense which may be incurred or suffered as a result of the use of this pamphlet.

© Magnet Mart 2007

**Magnet**  
MART  
Home  
Warehouse

**Phillip** Hindmarsh Dr Ph 6281 1744 Fax 6285 2493  
**Belconnen** Lathlain St Ph 6251 4622 Fax 6253 1087  
**Gungahlin** Crinigan Cir Ph 6228 9300 Fax 6228 9311  
**Queanbeyan** Yass Rd Ph 6297 8711 Fax 6299 2226  
**Goulburn** Sloane St Ph 4821 3533 Fax 4821 7347  
**Bowral** Bong Bong St Ph 4861 2355 Fax 4862 1066  
**Albion Park** Durgadin Dr Ph 4230 300 Fax 4230 3050

- Easy to follow step-by-step guide
- Important and handy tips
- Materials check list
- Project Cost Estimator


Before you start, please read through this pamphlet carefully and estimate and assemble all the materials you will need for the project and gather your tools and equipment together. Refer to the checklist and estimating form on the back panel of the pamphlet to assist in this preparation.

## You Can Install a Rainwater Tank

### Common Poly Tanks

Rainwater tanks can be made from galvanised steel, concrete or polyethylene (plastic). At Magnet Mart you will find a wide range of poly tanks that will suit most applications from large rural sizes through to under-eave tanks for the urban backyard.

This *Home Project* brochure will deal with installing the most common type of rainwater tank – the round poly tank. Please note that if you wish to connect your tank to internal plumbing such as a washing machine or toilet cistern, you will need to have the work performed by a licensed plumber.




A typical rainwater tank installation.

### Tank & Site Selection


Selecting the right size tank depends on how you intend to use the collected water. For example, if you wish to use the water for outdoor gardens and washing the car a 2,000 litre tank would be adequate. If you intend connecting the tank to the household plumbing for toilet flushing or use in a washing machine, the minimum size recommended in urban areas is 5,000 litres.

When siting the tank aim to place it on the southern side of the building as this will limit the amount of direct sunlight on the tank. Choose a site near an existing downpipe to make connecting the tank easier.

Site preparation for poly tanks is simply a matter of levelling an area and ensuring that no sharp rocks or projections remain near the surface immediately under the tank. Lay a 50mm thick bed of sand to ensure that the tank settles in level and the risk of rocks is decreased.



As an alternative, smaller tanks may be mounted on a tank stand. Magnet Mart can special order tank stands to suit a range of poly tanks or you can build one yourself from treated timber. A tank stand gives extra height for the outlet tap, providing higher water flow pressure and also allows for some garden storage space underneath.



Typical tank stand

**Pigments** - cement oxides are commonly used to colour the render and come in a wide range of colours to suit just about any décor. Achieving the correct colour is tricky, so try an experimental batch and record the proportions of the mixture for later use. Always let a sample mix dry completely so you can see the finished colour and keep the amount of oxide in a mixture to less than 10% of the mass of cement used.

### Mixing the Render

You can do one of two things to achieve a good render mix - follow the recipe below and make your own, or buy a pre-mixed render product such as Melcann's Render-It and mix according to the instructions on the pack.

Assuming the wall is a standard brick or concrete block wall, the best render mixture is to measure by volume:

1 part cement, 1 part lime and 6 parts clean plasterer's sand.

Use a plastic bucket as your measure by filling to the very top and scraping away the excess material to leave the surface flat. Repeat for each ingredient until you have enough material to make a batch.



### Wheelbarrow Mixing

Measure all dry ingredients in the barrow and mix with a shovel until a uniform colour is achieved. If you intend using a colouring pigment, add according to the manufacturer's instructions.

Mound the material and form a crater in the centre of the mound.


Add water slowly to the crater, turning the material into the centre with the shovel.

Once all the water is thoroughly mixed in, mound the material again and repeat the process until a stiff mix is achieved.



Test by scooping a quantity up on a trowel, if the mix sits up it is ready. If the mixture is too sloppy, the render coat will shrink

and crack as it dries. Continue to turn the mixture over with the shovel for a couple of minutes to ensure all the sand is coated. Use the mixture immediately.



For larger projects, use a mechanical cement mixer. Read the manufacturer's instructions on how to use the cement mixer before you commence.

Load a quantity of render onto a plasterer's hawk or a piece of ply or cement sheet and hold against the wall surface.




Using a steel plasterer's float, push some render onto the wall and spread across a small section to a thickness of around 10mm. Ensure the render is fully worked into the mortar joints between the bricks.



Continue this process until you have built up a covering of around 10mm thick over an area of 1 square metre. Your last strokes with the trowel should be smooth arcs.




Take care around windows, vents and weepholes in the wall, do not cover them with render mix. As you move across the wall, keep the surface damp with a water mist sprayed from a bottle. Render adheres best to damp, but not dripping bricks.




Usually, one coat of render is sufficient for most walls. In some circumstances you will need to add a second coat to cover imperfections or strong base colours.

#### Follow these steps to prepare for a second coating:

Wait for two hours after finishing the first coat of render, then 'key' the surface of the new render using a nail to scratch a criss-cross pattern.




For large wall surfaces, make up a 'rake' using a piece of scrap timber and nails. Space the nails every 25mm across the timber and ensure that they are driven through the timber to protrude an equal distance through the other side.



Use the rake to scratch the criss-cross pattern on the wall.

When keying is completed, allow the first coat to harden for 24 to 36 hours. Ensure




that the render does not dry out by misting the surface lightly with a spray bottle and covering with plastic drop sheets to reduce evaporation.




#### Applying the Second Coat

Mix the render as above and apply as you did for the first coat, ensuring that the second layer is thick enough to cover any imperfections.

For a different surface finish, apply the second coating with a timber trowel, smoothing off in sweeping arcs that leave a pleasant surface texture.



Leave the completed wall for at least seven days if you are considering painting.



#### Finishing Touches

Add a few terracotta urns, pots and planters to add to the Mediterranean feel of a rendered garden wall.

For a more rustic look, finish the render with a ball of damp hessian or heavy duty sponge, wiping in a swirly pattern.


Other finish textures can be achieved using a stiff brush or broom either drawn across the damp render surface, or lightly patting the surface to produce a textured effect.

Creating Textures



Hessian Method

Brush Stippling



Broom effect